

RUBBER SHEETING FOR MECHANICAL STRESS 7749 — SBR



INTERIOR	1.19 g/cm³	-25 – +80 °C	70 +/- 5 Sh A	300 %	10 MPa	1-15 mm
ENVIRONMENT	DENSITY	TEMPERATURE RANGE	HARDNESS	ELONGATION	TENSILE STRENGTH	THICKNESS

Sealing plate for general use with the added property of increased tensile strength. Suitable for environments without special requirements for resistance to negative influences. Made on the basis of SBR rubber compound with various chemical and physical-mechanical properties. With the possibility of specifying the required thickness (1 - 15 mm), width (1,200 - 1,400 mm) and number of inserts (0 - 2 pcs).



RESISTANCE

- Weather resistance NO
- Ozone resistance NO
- UV resistance NO
- Alkaline resistance MEDIUM RESISTANT
- Acid resistance MEDIUM RESISTANT
- Oil resistance NO
- Gasoline resistance NO

CONFIGURATION OPTIONS

THICKNESS

1 mm	(+/- 0,2 mm)
1.5 mm	(+/- 0,2 mm)
2 mm	(+/- 0,2 mm)
3 mm	(+/- 0,3 mm)
4 mm	(+/- 0,4 mm)
5 mm	(+/- 0,5 mm)
6 mm	(+/- 0,5 mm)
8 mm	(+/- 0,6 mm)
10 mm	(+/- 0,6 mm)
12 mm	(+/- 1,0 mm)
15 mm	(+/- 1,0 mm)

WIDTH

1200 mm	(+/- 10 mm)
1400 mm	(+/- 10 mm)

LENGTH

20 m	(+/- 200 mm)
10 m	(+/- 200 mm)
5 m	(+/- 200 mm)

NUMBER OF REINFORCEMENT LAYERS

without reinforcement	(for thicknesses 1 - 15 mm)
.....	
1 reinforcement layer	(for thicknesses 2 - 15 mm)
2 reinforcement layers	(for thicknesses 3 - 15 mm)