

# RUBBER SHEETING FOR GENERAL USE 7887 — CR-SBR



<b>INTERIOR</b>	1.3 <b>g/cm<sup>3</sup></b>	-25 – +80 <b>°C</b>	50 +/- 5 <b>Sh A</b>	300 <b>%</b>	6 <b>MPa</b>	1-6 <b>mm</b>
<b>ENVIRONMENT</b>	<b>DENSITY</b>	<b>TEMPERATURE RANGE</b>	<b>HARDNESS</b>	<b>ELONGATION</b>	<b>TENSILE STRENGTH</b>	<b>THICKNESS</b>

Sealing plate intended for general use without special requirements for resistance to negative environmental influences. Made on the basis of the SBR rubber compound in black. With the possibility of specifying the required thickness (1 - 6 mm), width (1,200 - 1,400 mm) and number of inserts (0 - 2 pcs). Click and choose. Complete the exact specification in the configurator.



## RESISTANCE

Weather resistance	MEDIUM RESISTANT
Ozone resistance	NO
UV resistance	MEDIUM RESISTANT
Alkaline resistance	MEDIUM RESISTANT
Acid resistance	MEDIUM RESISTANT
Oil resistance	NO
Solvent resistance	MEDIUM RESISTANT
Gasoline resistance	NO

## CONFIGURATION OPTIONS

THICKNESS	
1 mm	(+/- 0,2 mm)
1.5 mm	(+/- 0,2 mm)
2 mm	(+/- 0,2 mm)
3 mm	(+/- 0,3 mm)
4 mm	(+/- 0,4 mm)
5 mm	(+/- 0,5 mm)
6 mm	(+/- 0,5 mm)

WIDTH	
1200 mm	(+/- 10 mm)
1400 mm	(+/- 10 mm)

LENGTH	
20 m	(+/- 200 mm)
10 m	(+/- 200 mm)

NUMBER OF REINFORCEMENT LAYERS	
without reinforcement layers	(for thicknesses 1 - 6 mm)
.....	
1 reinforcement layer	(for thicknesses 2 - 6 mm)
.....	
2 reinforcement layers	(for thicknesses 3 - 6 mm)