7887 — CR-SBR

RUBBER SHEETING FOR GENERAL USE
7887 — CR-SBR

[redacted]

ENVIRONMENT	DENSITY	TEMPERATURE RANGE	HARDNESS	ELONGATION	TENSILE STRENGTH	THICKNESS
INTERIOR	1.3 g/cm³	-25 – +80 °C	50 +/- 5 Sh A	300 %	6 MPa	1 -6 mm

Sealing plate intended for general use without special requirements for resistance to negative environmental influences. Made on the basis of the SBR rubber compound in black. With the possibility of specifying the required thickness (1 - 6 mm), width (1,200 - 1,400 mm) and number of inserts (0 - 2 pcs). Click and choose. Complete the exact specification in the configurator.



RESISTANCE

Weather resistance	MEDIUM RESISTANT
Ozone resistance	NO
UV resistance	MEDIUM RESISTANT
Alkaline resistance	MEDIUM RESISTANT
Acid resistance	MEDIUM RESISTANT
Oil resistance	NO
Solvent resistance	MEDIUM RESISTANT
Gasoline resistance	NO

CONFIGURATION OPTIONS

THICKNESS

1 mm	(+/- 0,2 mm)
1.5 mm	(+/- 0,2 mm)
2 mm	(+/- 0,2 mm)
3 mm	(+/- 0,3 mm)
4 mm	(+/- 0,4 mm)
5 mm	(+/- 0,5 mm)
6 mm	(+/- 0,5 mm)

WIDTH

1200 mm	(+/- 10 mm)
1400 mm	(+/- 10 mm)

LENGTH

20 m	(+/- 200 mm)
10 m	(+/- 200 mm)

NUMBER OF REINFORCEMENT LAYERS

without reinforcement layers	(for thicknesses 1 - 6 mm)
1 reinforcement layer	(for thicknesses 2 - 6 mm)
2 reinforcement layers	(for thicknesses 3 - 6 mm)

BOGUMA, Ltd., Továrenská 314, 956 18 Bošany, Slovak Republic
Business Register Record, Trenčín, Section Ltd., Record No. 19109/R
IČO: 35 922 087, IČ DPH: SK2021963625
Billing Information: SK52 0900 0000 0052 4549 4451, SWIFT: GIBASKBX
Tel.: +421 38 5426 307, +421 38 5426 308, sales@boguma.sk, www.boguma.sk