

RUBBER SHEETING FOR GENERAL USE 7993 — SBR



| | | | | | | |
|--------------------|-------------------|--------------------------|----------------------|-------------------|-------------------------|------------------|
| INTERIOR | 1.47 g/cm³ | -25 - +80 °C | 65 +/- 5 Sh A | 200 % | 4 MPa | 1-15 mm |
| ENVIRONMENT | DENSITY | TEMPERATURE RANGE | HARDNESS | ELONGATION | TENSILE STRENGTH | THICKNESS |

Sealing plate intended for general use without special requirements for resistance to negative environmental influences. Made on the basis of the SBR rubber compound in black. With the possibility of specifying the required thickness (1 - 15 mm), width (1,200 - 1,400 mm) and number of inserts (0 - 2 pcs). Click and choose. Complete the exact specification in the configurator.



RESISTANCE

- Weather resistance NO
- Ozone resistance NO
- UV resistance NO
- Alkaline resistance NO
- Acid resistance NO
- Oil resistance NO
- Gasoline resistance NO

CONFIGURATION OPTIONS

THICKNESS

| | |
|--------|--------------|
| 1 mm | (+/- 0,2 mm) |
| 1.5 mm | (+/- 0,2 mm) |
| 2 mm | (+/- 0,2 mm) |
| 3 mm | (+/- 0,3 mm) |
| 4 mm | (+/- 0,4 mm) |
| 5 mm | (+/- 0,5 mm) |
| 6 mm | (+/- 0,5 mm) |
| 8 mm | (+/- 0,6 mm) |
| 10 mm | (+/- 0,6 mm) |
| 12 mm | (+/- 1,0 mm) |
| 15 mm | (+/- 1,0 mm) |

WIDTH

| | |
|---------|-------------|
| 1200 mm | (+/- 10 mm) |
| 1400 mm | (+/- 10 mm) |

LENGTH

| | |
|------|--------------|
| 20 m | (+/- 200 mm) |
| 10 m | (+/- 200 mm) |
| 5 m | (+/- 200 mm) |

NUMBER OF REINFORCEMENT LAYERS

| | |
|------------------------------|-----------------------------|
| without reinforcement layers | (for thicknesses 1 - 15 mm) |
| | |
| 1 reinforcement layer | (for thicknesses 2 - 15 mm) |
| 2 reinforcement layers | (for thicknesses 3 - 15 mm) |